

Bondfilm™ 8810 is a thermoplastic film adhesive used to produce a temporary bond. Once bonded, parts can be separated by reheating or immersion in a solvent.

*“A Reliable
and Responsive
Adhesive
Company.”*

Adhesive Properties

Color: Cream

Lap Shear Strength @ 75°C (Al to Al): 800 psi

Shelf Life: 1 year @ 5°C

ASSEMBLY

1. Remove separator paper from the temporary film adhesive.
2. Place Bondfilm™ 8810 between the parts to be bonded and apply pressure.
3. Heat the bonded parts to 95°C.
4. Allow the parts to cool to room temperature

DIS-ASSEMBLY

Reheat the parts to 95°C, while still heated, separate the parts from the adhesive layer. Any remaining adhesive residue may be dissolved using acetone, methyl ethyl ketone or tetrahydrofuran.

Parts can also be dis-assembled by immersing them in one of the afore mentioned solvents. This method only works with adhesive bonds less than 0.5 inch in width.

Adhesive properties are not intended to be used as specification limits.

Bondline™

Electronic Adhesives, Inc.

756 N. Pastoria Avenue, Sunnyvale, CA 94085 USA
Phone: 408-830-9200 Fax: 408-830-9266 Website: www.bondline.net

Rev.02/02/04

INSTRUCTIONS:

Place film adhesive between surfaces to be bonded. Apply continuous pressure of 1-5 psi during cure, using weight or spring loaded clamp.

AVAILABILITY:

Bondfilm™ 8810 epoxy film is available in sheet stock and die cut preforms. Die cut preforms are cut to customer specifications. Width and length tolerances are $\pm .005$ inch. Thickness tolerance $\pm .001$ inch.

STORAGE LIFE:

Storage life is 1 year at -40°C or colder.

CAUTION: For industrial use only. People with sensitive skin may have a reaction to this adhesive. Avoid skin contact. Wash all areas with soap and water immediately if contact does occur. It is important to refer to Material Safety Data Sheet (MSDS) OSHA for more details.

Bondline™
Electronic Adhesives, Inc.

2450 Kruse Drive, San Jose, CA 95131-1233 USA, Phone: 408-434-0400, Fax: 408-434-0585, www.bondline.net

© Bondline Electronic Adhesives, Inc. All rights reserved. All trademarks and registered trademarks belong to their respective owners. Notice to User: The information contained herein is based on technical data and tests which we believe reliable. It should be used by persons who have technical skill, at their own discretion and risk. Since conditions of use are outside of Bondline's control, we can assume no liability of results obtained or damages incurred through the application of data presented. Bondline's sole liability is limited to refund of purchase price of any product shown to be defective.